

Precautions for Safe Use

• To use the battery safely and properly, be sure to read the instruction manual before use.



- For stationary batteries, ensure that the room is well ventilated so that the hydrogen concentration is 0.8% or less. Failure to do so may cause fire or explosion.
- Do not install the battery in a poorly-ventilated area where the hydrogen concentration becomes more than 0.8%, or near open flame. Doing so may cause fire or explosion.

∧ Caution -

- The service temperature range of the battery is from -15 to 45°C. Using the battery outside this range may accelerate deterioration or cause the battery to freeze or overheat, resulting in damage or deformation.
- Do not use this battery where it is exposed to direct sunlight. Doing so may cause the parts of the battery to deteriorate.
- Do not expose the battery to water or seawater. Doing so may cause damage to the battery or fire, or cause the terminals or connecting plates to corrode.
- Do not use the battery near a heat source. Doing so may cause damage to the battery or cause the battery life to shorten.
- Do not use the battery in dusty areas. Doing so may cause a short-circuit.
- . Charge the battery under the charging conditions recommended by Furukawa Battery. Failure to do so may result in insufficient charging, electrolyte leakage, temperature rise, explosion, deterioration in performance, or reduced service life.
- Install the battery horizontally with the terminals facing up and ensure that the battery is not tilted more than 90°. Failure to do so may cause electrolyte leakage.
- Ensure that the maximum discharge current is not exceeded for more than 1 minute for 3C (A) or for more than 5 seconds for 6C (A). Failure to do so may cause damage to the battery.
- · Periodically inspect the battery. If the results deviate from the standards specified in the instruction manual, follow the steps in the instruction manual. Using the battery with such deviations may cause damage to the battery, or burnout.



*Actual colors may differ slightly from those in the photo due to printing limitations.

· Contact Information

THE FURUKAWA BATTERY CO., LTD.

2-4-1 Hoshikawa, Hodogaya-ku, Yokohama, Kanagawa Prefecture 240-0006 Japan http://www.furukawadenchi.co.jp

• Information contained in this catalogue is current as of August 2010 and may be subject to change without notice. For detailed information, please contact the Industrial Equipment Sales Department.

Valve-regulated Stationary Lead-acid Batteries

MSE/HSE Series





Batteries are the energy source that supports the evolution of the advanced information society, as represented by the IT revolution.

"MSE Series" are the most suitable batteries for use in this advanced information society.

"MSE Series" are innovative valve-regulated stationary lead-acid batteries that do not require water refilling throughout their entire lives and have various other features.

Furukawa Battery confidently offers its customers MSE series batteries, which contribute to maintenance-saving and space-saving of the power unit.



HSE Series HSE-80-8 HSE-80-8

MSE Series



Applications

- UPS Communication Instrumentation devices
- Emergency lighting systems
- Operation of equipment in power plants and substations
- Disaster and crime prevention systems
- Engine start-up
- And more

Features

Significantly Reduced Maintenance Work

Oxygen gas generated while charging is absorbed by the negative plate, which has eliminated the need for water refilling under normal use. In addition, the adoption of a special alloy in the electrode pate grid has reduced self-discharge, eliminating the need for equalized charging. These series are easy to use.

High-performance with High-rate Discharge Characteristics

Special separators with low internal resistance have been adopted with reduced resistance for the conductive parts, providing excellent high-rate discharge characteristics.

Longer Battery Life with Advanced Battery Plate Technology

The improved battery plate quality and structure provide a longer expected life. HS-E Series batteries have a battery life of 5 to 7 years, but MSE Series batteries have an improved battery life of 7 to 9 years [25°C, 0.1C (A) discharge]. This has reduced the running cost and significantly increased the additional value. (The battery life depends on the service temperature. See the figure to the right.)

Designed with Safety in Mind

This battery has a closed structure with the electrolyte being absorbed into the plates and separators. In addition, this battery is equipped with an explosion-proof and acid mist-proof filter provided in case there is a recharger failure and the battery is overcharged.


Advanced Compact Design with Size Reduction by 30%

In addition to the compact body (the volume has been reduced by about 30% from the HS-E Series), HSE/MSE Series batteries do not require space for maintenance such as water refilling and specific gravity measurement, allowing for significant space savings.


Wide Range of Capacities Available

Batteries are available in a wide range of capacities from 50 Ah to 3,000 Ah. The capacity can be selected to suit the intended application.

Relationship between the temperature and battery life of the HSE and MSE Series



*These values are estimated based on accelerated life testing results, and are not guaranteed values.



	Part name	Material						
0	Positive plate	Lead-calcium alloy/active material						
0	Negative plate	Lead-calcium alloy/active material						
0	Separator	Non-woven glass fiber						
4	Control valve	Synthetic rubber						
0	Container	ABS resin						
0	Cell lid	ABS resin						
0	Terminal	Lead alloy						
8	Filter	Ceramic						

C And more

Sealing Principle of Valve-regulated Batteries


Lead-acid batteries, at the end of the charging cycle, decompose water in the electrolyte by electrolysis and generate oxygen gas from the positive plate and hydrogen gas from the negative plate.

To prevent these gases from leaking out of the battery, there is a need to reduce gas generation or absorb the gas in the battery.

Furukawa Battery's valve-regulated staticnary lead-acid batteries have the following sealing mechanism:

- The separators are made of a special material with high breathability (non-woven fine glass fiber), and the amount of electrolyte used is limited to a minimum, allowing the gases to pass between the positive and negative plates.
- At the end of the charging cyce, the oxygen gas generated from the positive plate goes through the separators and reaches the negative plate. The oxygen gas then oxidizes sponge lead (Pb), which is a negative active material, to form lead oxide on the negative plate, ceasing to exist as a gas.
 - Note: In the charged state, the negative active material (Pb) is extremely easily oxidized. In other words, the negative active material easily abscrbs the oxygen gas.
- The oxide lead (PbO) formed on the negative plate reacts immediately with the electrolyte (H₂SO₄) to form lead sulfate (PbSO₄), which is the active material in the dscharged state, and water (H₂O). This means that the negative plate is partially discharged when it absorbs oxygen.

Sealing Principle of Valve-regulated Batteries



- If charging continues, the lead sulfate (PbSO4) will be reduced to sponge lead (Pb), but the negative plate will be partially discharged again by the oxygen.
- At the end of the charging cycle, as mentioned above, the negative plate is charged and discharged repeatedly in equilibrium, preventing hydrogen gas from being generated.
- At the same time, the oxygen gas generated from the positive plate is absorbed by the negative plate and ceases to exist as a gas, meaning that for all intents and purposes no water is discomposed by electrolysis. This allows the water content in the electrolyte to be maintained at almost the same level.
- During this time, the internal pressure in the battery increases a little, but the battery container is designed to withstand the pressure increase.

If the battery is charged with a large current and the gas absorption capacity is exceeded, causing the internal pressure to increase the control valve wll operate to relieve the pressure.

In addition, the control valve prevents the negative plate from being oxidized due to ar intrusion and prevents the evaporation of the water.


Gas-generating reaction on the positive plate

$$H_2O \rightarrow 2H^+ + \frac{1}{2}O_2 \uparrow + 2e^-$$

Gas-absorbing reaction on the negative plate

Pb+
$$\frac{1}{2}$$
O₂→PbO
PbO+H₂SO₄→PbSO₄+H₂O
PbSO₄+2H⁺+2e⁻→Pb+H₂SO₄

Single-cell Requirements



HSE Series

14-4-1	Nominal	Capac	ity (Ah)	Dim	Mass	Outline		
Model	voltage (V)	10-hour rate	1-hourrate	H (max.)	W (approx.)	L (approx.)	(approx. kg)	drawing
HSE-30-12	12	30	18	220	128	235	14	0
HSE-40-12	12	40	24	220	128	299	17	0
HSE-50-12	12	50	30	220	128	363	20.5	0
HSE-60-6	6	60	36	220	128	217	13	0
HSE-80-6	6	80	48	220	128	281	17	0
HSE-100-6	6	100	60	220	128	345	20	0


MSE Series


NA 1	Nominal	Capac	ity (Ah)	Dim	Mass	Outline		
Model	voltage (V)	10-hour rate	1-hourrate	H (max.)	W (approx.)	L (approx.)	(approx. kg)	drawing
MSE-50-12	12	50	32.5	220	128	363	20.5	0
MSE-100-6	6	100	65	220	128	345	20	0
MSE-150	2	150	97.5	365	170	106	12	0
MSE-200	2	200	130	365	170	106	15	0
MSE-300	2	300	195	365	170	150	21	0
MSE-500	2	500	325	365	171	241	35	9
MSE-1000	2	1000	650	365	171	471	70	6
MSE-1500	2	1500	975	375	337	476	108	6
MSE-2000	2	2000	1300	375	337	476	139	6
MSE-3000	2	3000	1950	375	340	696	209	0

lequired capacity (Ah/10 hr)	Combinations
50	MSE-50-12
100	MSE-100-6
150	MSE-150
200	MSE-200
300	MSE-300
400	MSE-200×2
500	MSE-500
600	MSE-300×2
700	MSE-200+MSE-500
800	MSE-300+MSE-500
900	MSE-300×3
1000	MSE-1000
1100	MSE-300×2+MSE-500
1200	MSE-200+MSE-500×2
1300	MSE-300+MSE-500×2
1500	MSE-1500
2000	MSE-2000
2500	MSE-1000+MSE-1500
3000	MSE-3000

Battery Rack Requirements







	One-tier rack Two-tier rack											Three-tier rack									
Battery			Two	rows			One	row	Two	rows	Three	rows	Four	rows			Two rows F		Four	Four rows	
model	Hı	Hz	Wı	Ms	Hi	H₂	Wı	Wг	Wı	W2	Wı	Ms	Wı	Wa	Hı	H₂	Wı	Wг	Wı	M ⁵	
MSE-150 MSE-200	528	343	552	552	1216	1031	316	316	552	552	808	798	1044	1034	1749	1564	572	562	1044	1034	
MSE-300	528	343	552	552	1216	1031	316	316	552	552	808	798	1044	1034	1749	1564	572	562	1044	1034	
MSE-500	543	358	694	694	1246	1061	407	397	714	704	1021	1011	1328	1318	1794	1609	714	704	1328	1318	
MSE-1000	543	358	1174	1164	1246	1061	637	627	1174	1164	_	_	_	_	1794	1609	1269	1244	_	_	
MSE-1500	553	368	1184	1174	1266	1081	672	647	1279	1254	_	_	-	_	1824	1639	1279	1254	_	_	
MSE-2000	553	368	1184	1174	1266	1081	672	647	1279	1254	_	_	_	_	1824	1639	1279	1254	_	_	
MSE-3000	553	368	1624	1614	1266	1081	892	867	1723	1694	-		_	_	1824	1639	1749	1714	_	_	

lotes 1) For battery racks indicated with a Δ, dimension E is 1	50.	
-----------------------------------------------------------------	-----	--

Other racks shapes are available.

5

Number of cells per row												
5	6	7	8	9	10	11	12	13	14	15	16	
L	L	L	L	L	L	L	L	L	L	L	L	E
S	S	S	S	S	S	S	S	S	S	S	S	
×n	Xn	×n	Xn	×n	×n	×n	×n	×n	×n	×n	×n	
△630 330 ×1	△741 441 ×1	△852 552 ×1	△963 663 ×1	△1074 774 ×1	1185 755 ×1	1296 866 ×1	1407 977 ×1	1518 544 ×2	1629 599.5 ×2	1740 655 ×2	1851 710.5 ×2	215 △150
△850 550 ×1	△1005 705 ×1	1160 730 ×1	1315 885 ×1	1470 520 ×2	1625 597.5 ×2	1780 675 ×2	1935 752.5 ×2	2090 830 ×2	2245 907.5 ×2	2400 656.7 ×3	2555 708.3 ×3	215 △150
950	1125	1300	1475	1650	1825	2000	2175	2350	2525	2700	2875	215
520	695	870	522.5	610	697.5	785	872.5	640	698.3	756.6	815	
×1	×1	×1	×2	×2	×2	×2	×2	×3	×3	×3	×3	
950	1125	1300	1475	1650	1825	2000	2175	2350	2525	2700	2875	215
520	695	870	522.5	610	697.5	785	872.5	640	698.3	756.6	815	
×1	×1	×1	×2	×2	×2	×2	×2	×3	×3	×3	×3	
1785	2127	2469	2811	3153	3495	3837	4179	4521	4863	5205	5547	215
677.5	848.5	679.7	793.7	907.7	766.3	851.8	749.8	818.2	886.6	795.8	852.8	
×2	×2	×3	×3	×3	×4	×4	×5	×5	×5	×6	×6	
1785	2127	2469	2811	3153	3495	3837	4179	4521	4863	5205	5547	215
677.5	848.5	679.7	793.7	907.7	766.3	851.8	749.8	818.2	886.6	795.8	852.8	
×2	×2	×3	×3	×3	×4	×4	×5	×5	×5	×6	×6	
1800	2145	2490	2835	3180	3525	3870	4215	4560	4905	5250	5595	215
685	857.5	685.7	801.7	916.7	773.8	860	757	826	895	803.3	860.8	
×2	×2	×3	×3	×3	×4	×4	×5	×5	×5	×6	×6	

Knock-down type Material: mild steel


Standard color: Munsell No. 5Y7/1, semi-gloss Acid-resistant coating Seismic resistance: Static horizontal acceleration 1 G

³⁾ All dimensions are given in millimeters.


⁴⁾ The anchor bolt locations are given as reference values.

Characteristics







HSE Series Discharge Current-Capacity Characteristics




MSE Series Temperature-Capacity Characteristics




HSE Series Temperature-Capacity Characteristics



MSE Series Discharge Characteristics with Varying Discharge Rate



HSE Series Discharge Characteristics with Varying Discharge Rate



*"C" indicates the value of the rated capacity at a 10-hour rate.

Comparison between Valve-regulated and Catalytic Plug Batteries

		Valve-regulated batteries	Catalytic plug batteries				
Ма	intenance-saving (principle)	At the end of the charging cycle, the oxygen gas generated from the positive plate is absorbed by the negative plate, ceasing to exist as a gas. At the same time, the negative plate is kept in a discharged state, by means of a chemical reaction, so as to prevent hydrogen gas from being generated.	At the end of the charging cycle, the water in the electrolyte is decomposed by electrolysis to form oxygen and hydrogen gases. These gases are guided to the catalytic plug and recombined by catalysis to form water, which is circulated in the cell.				
Ма	intenance-saving (structure)	Using special separators and keeping the amount of electrolyte used to a minimum allows the gases to pass between the positive and negative plates, enabling the negative plate to absorb the gases more efficiently.	A catalytic plug is installed onto the vent of a vente battery (CS, HS).				
	Plate types	Paste type (HSE) Paste type (MSE) Lead-calcium alloy	Clad type (CS-E) Paste type (HS-E) Lead-antimony alloy				
Capacity range		Paste type HSE 12V:30Ah~50Ah 6V:60Ah~100Ah Paste type MSE 12V:50Ah 6V:100Ah 2V:150Ah~3000Ah	Clad type 2V:15Ah~2400Ah 6V:15Ah~90Ah Paste type 2V:30Ah~2500Ah 6V:30Ah~120Ah				
stics	High-rate discharge characteristics	HSE Series: Excellent MSE Series: Extremely excellent	Clad type: Normal Paste type: Excellent				
Characteristics	Self-discharge rate	0.1% or less per day	0.5% or less per day				
Cha	Expected life (25°C)	HSE Series: about 5 to 7 years MSE Series: about 7 to 9 years	Clad type: 10 to 14 years Paste type: 5 to 7 years				
Ф	Float voltage	2.23 V per cell (Constant voltage available)	Clad type: 2.15 V per cell Paste type: 2.18 V per cell				
anc	Equalizing charge frequency	Not required	Once every 3 to 6 months				
ten	Water refilling frequency	Not required	Once every 3 to 5 years				
Maintenance	Specific gravity measurement	Not required	Once a month				
~	Electrolyte level check	Not required	Required (The electrolyte level decreases slightly.)				
	Parts replacement	Not required	Catalytic plug: Requires replacement every 3 to 5 years.				
	Volume ratio	60~70	100				
Inst	allation area ratio	60~70	100				







7

